



STEELCUT TRIO 2

TISSU | FABRIC




105




205



213




113




713



245




133



153




325




253




325




253




383



124









353



195










STEELCUT TRIO 2

TISSU | FABRIC





STEELCUT TRIO 2

TISSU | FABRIC



STEELCUT TRIO 2

TISSU | FABRIC



STEELCUT TRIO 2

TISSU | FABRIC

DESCRIPTION

Tissu d'ameublement pour am  nagement priv   et public. Grande r  sistance.

Offices, hotels, institutions and domestic use. Great durability.

COMPOSITION

90% Laine vierge paign  e, 10% Nylon.

100% New wool, worsted. 10% Nylon.

DETAILS

	M��THODE / TEST METHOD	VALEUR / LIMIT VALUE
Poids / Weight	-	770 g/m ²
Largeur / Width	-	140 cm
R��sistance �� l'abrasion Abrasion resistance	UNI EN ISO 12947	80.000 cycles Martindale
Normes au feu Flammability	En 1021-1/2	Source d'ignition 0 et 1 Part 0 and 1
	BS 5852	Source d'ignition 2 et 3 Part 2 and 3

ENTRETIEN CLEANING

Aspirer r  guli  rement ou nettoyage    sec.

Vacuum regularly or professional dry clean.